Amendments to the Claims:

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

1. (Currently amended) A polyol prepolymer chain extender for a silicone modified polyurea comprising the reaction product of:

at least one amine; and at least one branched epoxy functional silicone containing a phenyl group.

- 2. (Original) The polyol prepolymer chain extender of claim 1 wherein said at least one amine is selected from the group consisting of primary aliphatic amines, primary cyclo-aliphatic, secondary aliphatic amines, primary aromatic amines, and secondary aromatic amines, and mixtures thereof.
- 3. (Currently amended) The polyol prepolymer chain extender of claim 1 wherein said epoxy functional silicone is a silicone modified epoxy resin that has the general formula:

Serial No. 10/648,934
Amendment and Remarks Responsive To
Office Action Mailed 05/13/05
Page 3 of 17

Nov-03-2005 18:31

wherein x is an integer from about 1 to about 100, y is an integer from about 1 to about 100, and z is an integer from about 1 to about 100.

- 4. (Currently amended) The polyol prepolymer chain extender of claim 1 wherein said at least one amine is present in the range of from about 50 20 to about 900 95 parts by weight, based on 100 parts by weight of the total polyol prepolymer chain extender.
- 5. (Currently amended) The polyol prepolymer chain extender of claim 1 wherein said at least one epoxy functional silicone is present in the range of from about 50 5 to about 200 80 parts by weight, based on 100 parts by weight of the total polyol prepolymer chain extender.
- 6. (Currently amended) The polyol prepolymer chain extender of claim 1 wherein said at least one amine is a combination of from about 450 20 to about 450 75 parts by weight of a polyoxypropylenediamine that has a formula:

x = 5.6

Serial No. 10/648,934 Amendment and Remarks Responsive To Office Action Mailed 05/13/05 Page 4 of 17 and from about 250 25 to about 750 80 parts by weight of a diethyltoluenediamine (DETDA), based on 100 parts by weight of the total polyol prepolymer chain extender wherein x equals 5.6.

7. (Currently amended) The polyol prepolymer chain extender of claim 1 wherein said at least one amine is a combination of from about 450 20 to about 450 75 parts by weight of a polyoxypropylenediamine that has a formula:

x = 5.6

and from about 250 25 to about 750 80 parts by weight of a dimethylthiotoluene diamine (DMTDA), based on 100 parts by weight of the total polyol prepolymer chain extender wherein x equals 5.6.

8. (Currently amended) The polyol prepolymer chain extender of claim 1 wherein said at least one amine is a combination of from about 450 20 to about 450 70 parts by weight of a polyoxypropylenediamine that has a formula:

x = 5.6

and from about 200 30 to about 600 80 parts by weight of a polyaspartic ester, based on 100 parts by weight of the total polyol prepolymer chain extender wherein x equals

Serial No. 10/648,934 Amendment and Remarks Responsive To Office Action Mailed 05/13/05 Page 5 of 17 5.6.

- The polyol prepolymer chain extender as in (Currently amended) 9. one of claims 6-8, in which said epoxy functional silicone is from about 50 ± 4 to about 150 38 parts by weight of silicone modified epoxy resin, based on 100 parts by weight of the total polyol prepolymer chain extender.
 - (Withdrawn) A silicone modified polyurea comprising: 10.
- a B-component which includes at least one polyol prepolymer chain extender which comprises:

at least one amine;

at least one epoxy functional silicone; and

an A-component which comprises at least one polyisocyanate.

- (Withdrawn) The silicone modified polyurea of claim 10 wherein said at 11. least one amine is selected from the group consisting of primary aliphatic amines, primary cyclo-aliphatic, secondary aliphatic amines, primary aromatic amines, and secondary aromatic amines, or a combination of said amines.
- (Withdrawn) The polyol prepolymer chain extender of claim 1 wherein 12. said epoxy functional silicone is a silicone modified epoxy resin that has the general formula:

Serial No. 10/648,934 Amendment and Remarks Responsive To Office Action Mailed 05/13/05 Page 6 of 17

Serial No. 10/648,934 Amendment and Remarks Responsive To Office Action Mailed 05/13/05

348345v1

aliphatic isocyanates selected from the group consisting of hexamethylene diisocyanate (HMDI); a bifunctional monomer of tetraalkyl xylene diisocyanate; cyclohexane diisocyanate; 1,12-dodecane diisocyanate; 1,4-tetramethylene diisocyanate; isophorone diisocyanate (IPDI); and dicyclohexylmethane diisocyanate;

aromatic isocyanates selected from the group consisting of m-phenylene diisocyanate; p-phenylene diisocyanate; polymethylene polyphenylene diisocyanate; 2,4-toluene diisocyanate; 2,6-toluene diisocyanate; dianisidine diisocyanate; bitolylene diisocyanate; naphthalene-1,4-diisocyanate; and diphenylene 4,4'-diisocyanate; and

aliphatic/aromatic diisocyanates, selected from the group consisting of xylylene-1,3-diisocyanate; bis(4-isocyanatophenyl)methane; bis(3-methyl-4-isocyanatophenyl)methane; and 4,4'-diphenylpropane diisocyanate; tetramethyl xylene diisocyanate (TMXDI); and mixtures thereof.

- 14. (Withdrawn) The silicone modified polyurea of claim 10 wherein said B-component further comprises UV stabilizers.
- 15. (Withdrawn) The silicone modified polyurea of claim 10 wherein said B-component further comprises color pigments.
- 16. (Withdrawn) The silicone modified polyurea of claim 10 wherein said B-component further comprises silane coupling agents.
- 17. (Withdrawn) The silicone modified polyurea of claim 10 wherein said B-component further comprises fire retardants.
- 18. (Currently amended) A method of making a polyol prepolymer chain extender for a silicone modified polyurea comprising:

Serial No. 10/648,934
Amendment and Remarks Responsive To
Office Action Mailed 13 May 2005
Page 8 of 17

Nov-03-2005 16:32

combining an adduct excess of at least one amine selected from the group consisting of primary aliphatic amines, primary cyclo-aliphatic, secondary aliphatic amines, primary aromatic amines, and secondary aromatic amines, and mixtures thereof, with at least one <u>branched</u> epoxy functional silicone <u>containing a phenyl group</u> to form a solution; and

reacting said solution to form a polyol prepolymer chain extender, wherein said reacting comprises heating said solution at a temperature in the range of from 130°F. to 210°F, for a time period of from 1 hour to 24 hours.

- 19. (Original) The method of claim 18 wherein said epoxy functional silicone is a silicone modified epoxy resin.
- 20. (Withdrawn) A method of making a silicone modified polyurea comprising: combining an adduct of at least one amine selected from the group consisting of primary aliphatic amines, primary cyclo-aliphatic, secondary aliphatic amines, primary aromatic amines, and secondary aromatic amines, and mixtures thereof, with at least one epoxy functional silicone to form a solution;

reacting said solution to form a polyol prepolymer chain extender, wherein said reacting comprises heating said solution at a temperature in the range of from 130°F. to 210°F, for a time period of from 1 hour to 24 hours; and

mixing said polyol prepolymer chain extender with at least one polyisocyanate to form a silicone modified polyurea.

- 21. (Withdrawn) The method of claim 20 wherein said mixing is performed by a pressurizable spray apparatus.
- 22. (Withdrawn) A method of applying a silicone modified polyurea to a substrate, comprising:

combining an adduct of at least one amine selected from the group consisting of

Serial No. 10/648,934
Amendment and Remarks Responsive To
Office Action Mailed 13 May 2005
Page 9 of 17

primary aliphatic amines, primary cyclo-aliphatic, secondary aliphatic amines, primary aromatic amines, and secondary aromatic amines, and mixtures thereof, with at least one epoxy functional silicone to form a solution;

reacting said solution to form a polyol prepolymer chain extender, wherein said reacting comprises heating said solution at a temperature in the range of from 130°F, to 210°F, for a time period sufficient to substantially react all of said polyol prepolymer chain extender;

cooling said polyol prepolymer chain extender; and

applying said polyol prepolymer chain extender and said at least one polyisocyanate simultaneous to said substrate to form a silicone modified polyurea on said substrate.

- 23. (Withdrawn) The method of claim 22 wherein said heating is in a temperature range of from 130°F. to 210°F.
- 24. (Withdrawn) The method of claim 22 wherein said substrate is prepared prior to application of said silicone modified polyurea.

Serial No. 10/648,934 Amendment and Remarks Responsive To Office Action Mailed 13 May 2005 Page 10 of 17